AMENDMENTS TO THE CLAIMS:

The listing of claims will replace all prior versions, and listings of claims in the application:

LISTING OF THE CLAIMS

- 1. (currently amended) A non-fiber reinforced polyolefin work piece having a thermoset coating adhered thereto made by a process comprising the steps of:
 - a. forming a polyolefin work piece in a closed mold;
- b. injecting a thermoset coating composition capable of free radical initiation into said closed mold such that said coating comes in contact with at least a portion of a surface of said work piece; and
- c. opening said mold and removing said work piece after said coating composition has at least partially cured; wherein said polyolefin is selected from the group consisting of polyolefin homopolymers, polyolefin copolymers, functionalized polyolefins, and blends thereof; and wherein wherein said thermoset coating comprises a saturated aliphatic polyester urethane intermediate, a saturated (cyclo) aliphatic (meth) acrylate, one or more hydroxy alkyl (meth) acrylates, a polyacrylate ester of an alkylene polyol, one or more vinyl substituted aromatics, and an initiator capable of generating free radicals in said coating composition.
- 2. (original) A work piece according to claim 1, wherein the polyolefin comprises an ethylene-propylene copolymer.
- 3. (original) A work piece according to claim 1, wherein the polyolefin comprises a copolymer of an olefin and an ethylenically-unsaturated monomer that is polar in nature.
- 4. (original) A work piece according to claim 3, wherein the polyolefin comprises a copolymer of an olefin and a monomer selected from the group consisting of vinyl esters of carboxylic acids, vinyl halides, and unsaturated carboxylic acids or esters thereof.

- 5. (original) A work piece according to claim 3, wherein the polyolefin comprises a copolymer of an olefin and a monomer selected from the group consisting of acrylic acid, methacrylic acid, carbon monoxide, methyl acrylate, butyl acrylate, methyl hydrogen maleate and vinyl acetate.
- 6. (original) A work piece according to claim 1, wherein the polyolefin comprises a functionalized polymer having an olefinic backbone and one or more monomers grafted to said backbone.
- 7. (original) A work piece according to claim 6, wherein said one or more monomers are selected from the group consisting of sulfur-, halogen-, oxygen- and/or nitrogen-containing ethylenically unsaturated, aliphatic or aromatic monomers having from 2 to about 50 carbon atoms.
- A work piece according to claim 7, wherein said one or more 8. (original) monomers are selected from the group consisting of methyl methacrylate; ethyl methacrylate; butyl methacrylate; octyl methacylate; methacrylic acid; methyl acrylate; ethyl acrylate; butyl acrylate; octyl acylate; 2-hydroxyethyl acrylate; glycidyl acrylate; acrylic acid; maleic anhydride; vinyl acetate; acrylonitrile; acrylamide; vinyl chloride; vinyl fluoride; vinylidenedifluoride; tetrafluoroethylene; styrene; alpha-methyl styrene; trimethoxyvinylsilane; triethoxyvinylsilane; N-vinylimidazole; 1-vinyl-2-pyrrolidinone; Cvinylimidazole; N-allylimidazole; 1-vinylpyrrolidinone; 2-vinylpyridine; 4-vinylpyridine; Nmethyl-N-vinylacetamide; diallyl formamide; N-methyl-N-allyl formamide; N-ethyl-N-allyl formamide; N-cyclohexyl-N-allyl formamide; 4-methyl-5-vinyl thiazole; N-allyl diisooctyl phenothiazine; 2-methyl-1-vinylimidazole; 3-methyl-1-vinylpyrazole; N-vinylpurine; Nvinylpiperidines; vinylmorpholines; and vinvlpiperazines: N-vinylsuccinimide aminopropylimidazole.
- 9. (original) A work piece according to claim 1, wherein the polyolefin comprises a blend of one or more polyolefin homopolymers, polyolefin copolymers, and functionalized polyolefins.

- 10. (original) A work piece according to claim 9, wherein the polyolefin comprises a blend of a polyolefin homopolymer, a polyolefin copolymer, or a functionalized polyolefin with an impact modifying polymer.
- 11. (original) A work piece according to claim 9, wherein the impact modifying polymer is a halogenated polymer.
- 12. (currently amended) A polyolefin work piece substantially free of fiber reinforcement having a thermoset coating adhered thereto made by a process comprising the steps of:
- a. introducing a polyolefin material into a closed mold to form a work piece;
- b. introducing into said closed mold a thermoset coating composition comprising a saturated aliphatic polyester urethane intermediate, a saturated (cyclo) aliphatic (meth) acrylate, one or more hydroxy alkyl (meth) acrylates, a polyacrylate ester of an alkylene polyol, one or more vinyl substituted aromatics, and an initiator capable of generating free radicals, said composition including a component capable of generating free radicals, said composition contacting at least a portion of a surface of said work piece, a surface temperature of said workpiece being at or above the temperature at which free radicals are generated in said coating composition; and
- c. opening said mold and removing said work piece after said coating composition has at least partially cured; wherein said polyolefin is selected from the group consisting of polyolefin homopolymers, polyolefin copolymers, functionalized polyolefins, and blends thereof.
- 13. (original) A work piece according to claim 12, wherein the work piece comprises less than 5% reinforcing fiber.
- 14. (original) A work piece according to claim 13, wherein the work piece is free of reinforcing fiber.
- 15. (currently amended) A work piece consisting essentially of polyolefin having a thermoset coating adhered thereto made by a process comprising the steps of:
 - a. introducing a polyolefin material heated to a temperature at or above

its melting point into a closed mold to form a work piece;

- b. introducing into said closed mold a thermoset coating composition comprising a saturated aliphatic polyester urethane intermediate, a saturated (cyclo) aliphatic (meth) acrylate, one or more hydroxy alkyl (meth) acrylates, a polyacrylate ester of an alkylene polyol, one or more vinyl substituted aromatics, and an initiator capable of generating free radicals including a component capable of generating free radicals to contact at least a portion of a surface of said work piece, the temperature of said surface being at or above the temperature at which free radicals are generated in said coating composition; and
- c. opening said mold and removing said work piece after said coating composition has at least partially cured; wherein said polyolefin material is selected from the group consisting of polypropylene, polyethylenes, polystyrenes, polybutylenes, substituted polyolefins and mixtures thereof.
- 16. (currently amended) A molded non-fiber reinforced polyolefin workpiece including a thermoset coating bonded thereto, said coating comprising a composition including a free radical generating component the reaction product of a saturated aliphatic polyester urethane intermediate, a saturated (cyclo) aliphatic (meth) acrylate, one or more hydroxy alkyl (meth) acrylates, a polyacrylate ester of an alkylene polyol, one or more vinyl substituted aromatics, and an initiator capable of generating free radicals in said coating composition.
- 17. (original) A molded polyolefin work piece according to Claim 16 wherein said component capable of generating free radicals is a peroxide initiator.
- 18. (canceled)
- 19. (original) A molded polyolefin work piece according to Claim 16 wherein said component capable of generating free radicals is an azo-initiator.
- 20. (original) A thermoplastic work piece substantially free of fiber reinforcement having a thermoset coating adhered thereto made by a process comprising the steps of:
 - a. forming a thermoplastic work piece in a closed mold;
 - b. introducing into said closed mold a thermoset coating composition

comprising a saturated aliphatic polyester urethane intermediate, a saturated (cyclo) aliphatic (meth) acrylate, one or more hydroxy alkyl (meth) acrylates, a polyacrylate ester of an alkylene polyol, one or more vinyl substituted aromatics, and an initiator capable of generating free radicals in said coating composition; and

- c. opening said mold and removing said work piece after said coating composition has at least partially cured.
- 21. (original) A work piece according to claim 20, wherein said thermoplastic is selected from the group consisting of polyolefin homopolymers, polyolefin copolymers, grafted polyolefins, and blends thereof.
- 22. (original) A work piece according to claim 20, wherein said thermoplastic is selected from the group consisting of nylon, polystyrenes, and substituted polyolefins.
- 23. (original) A work piece according to claim 20, wherein said mold is heated to a temperature of 200-250°F during steps a and b.
- 24. (original) A work piece according to claim 23, wherein said polyolefin is heated to a temperature of 400-500°F prior to introduction into said mold.
- 25. (original) A work piece according to claim 20, wherein said thermoset coating composition is injected into said mold at a pressure of 1000-5000 psi.
- 26. (original) A work piece according to claim 20, wherein said work piece is formed at an internal mold pressure of about 250 bar.